

## Acrylic thinner

### PRODUCT DESCRIPTION

DVA XY is a solvent blend designed for use with all acrylic based conformal coatings. Especially used for AVR80 XY acrylic coating.

The main uses of the thinners is to dilute the coatings for use in dip and spray coating.

### Spray Coating

When solvent based coatings are sprayed, the higher pressure at the nozzle forces the solvent within the coating to evaporate very quickly. Therefore, to avoid cob-webbing ( i.e. the coating drying immediately as it leaves the spray gun), extra solvent must be added.

DVA XY should be used at levels of between 1:1 and 1:3 (Coating:Thinners) depending upon the application.

To avoid microbubbles in the coating, stand 2 minutes before attempting to spray.

Thinners should be added gradually until a spray pattern is achieved without "cob-webbing" and the coating weight required is reached.

### Dip Coating

DVA XY may be used to maintain the viscosity of acrylic conformal coatings in open tanks used in dip coating processes. Over time the solvent within the coatings evaporates, increasing the viscosity of the coating, and giving a thicker coating. This solvent loss must be replaced to maintain the correct viscosity to give an economical coating thickness.

In most systems it is sufficient to measure the viscosity of the coating once per week.

DVA XY is a flammable solvent blend and should be used in a well ventilated area and all sources of ignition must be avoided.

Please refer to the separate Health & Safety Data Sheet for further details.

### PACKAGING

5 Litres

### ORDER CODE

DVA XY 05L

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

ABchimie cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

*Toutes ces informations sont données en toute bonne foi mais sans garantie. Chaque application étant différente, il est vivement conseillé d'effectuer des tests préalables. Les spécifications concernant les propriétés sont données à titre indicatif et non comme étant spécifiques.*